

	L #	Hits	Search Text	DBs
1	L1	0	((antireflection (anti adj reflection)) adj film) same (optical adj (fiber filament)) same dip\$4 same (end adj surface) same (pulling adj speed) same solution same relfection same wavelength	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
2	L2	772	((antireflection (anti adj reflection)) adj film) and (optical adj (fiber filament))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
3	L3	63	2 and dip\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
4	L4	2	3 and (pulling adj speed)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
5	L5	173	2 and (wavelength adj band)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
6	L6	5	5 and pulled	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
7	L7	0	6 and relfection	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
8	L8	5	6 and reflection	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
9	L9	1714	(optical adj (fiber filament)) and "427".clas.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
10	L10	1714	(optical adj (fiber filament)) and "427/".clas.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
11	L11	1398	10 and coat\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
12	L12	365	11 and dip\$5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB

13	L13	44	12 and pulled	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM TDB
----	-----	----	---------------	--

	L #	Hits	Search Text	DBs
14	L14	2	13 and (pulling adj speed)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
15	L15	4	12 and (pulling adj speed)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
16	L16	2	15 not 14	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
17	L17	2749 68	(optical adj (fiber filament))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
18	L18	772	17 and (((anti adj reflection) antireflection) adj film)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
19	L19	63	18 and dip\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
20	L20	51	19 and (solution coating composition bath)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
21	L21	8	20 and pulled	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
22	L22	8	20 and (pulled (pulling adj speed))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
23	L23	1213	takahashi-takashi.inv.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
24	L24	41	23 and 17	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
25	L25	2	24 and (((anti adj reflection) antireflection) adj film)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
26	L26	38	24 and (solution coating composition bath)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
27	L27	4	26 and dip\$4	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
28	L28	3	27 and (pulled (pulling adj speed))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT; IBM_TDB
29	L29	1	("5116644").PN.	USPAT